

## POWDER EYE SHADOW KPE-01AB

Powder treated with AMIAURA<sup>™</sup> TK-01A – TK-01B imparts high adhesion to eye shadow.

	Trade Name	INCI Name	wt%	Function
A	SUNSPHERE NP-200 *1	Silica	5.3	Sensory improver
	TAROX LL-100HP *2	Iron Oxides (CI77492)	1.1	Pigment
	TAROX R-516HP *2	Iron Oxides (CI77491)	1.1	Pigment
	TAROX BL-100HP *2	Iron Oxides (CI77499)	1.1	Pigment
в	AMIAURA™ TK-01A	Disodium Stearoyl Glutamate, Arginine, Glycerin, Water	1.2	Treatment agent
С	AMIAURA™ TK-01B	Calcium Chloride, Water	0.27	Treatment agent
D	SHP-5 *3	Boron Nitride	15.0	Sensory improver
	Magnesium Myristate *4	Magnesium Myristate	18.8	Binder
Е	TCG-M *5	Caprylic/capric Triglyceride	12.5	Emollient, Binder
F	Colorona Copper *6	Mica, Iron oxide	11.5	Pearl pigment
	Colorona Copper Sparkle *6	Mica, Iron oxide	11.5	Pearl pigment
	Colorona Bronze *6	Mica, Iron oxide	11.5	Pear pigment
G	AMIAURA™ TK-01A	Disodium Stearoyl Glutamate, Arginine, Glycerin, Water	2.6	Treatment agent
Н	AMIAURA™ TK-01B	Calcium Chloride, Water	0.56	Treatment agent
Ι	METASHINE MT1080RS *7	Calcium Sodium Borosilicate	6.3	Pearl pigment
		Total	100	

\*1 AGC Si-Tech, \*2 Titan Kogyo, \*3 JFE MINERAL & Alloy, \*4 Taihei Chemical Industrial,

\*5 Kokyu Alcohol Kogyo, \*6 MERCK, \*7 NSG

## <PROCEDURE>

- 1. Weigh Part A and mix with a mixer for 30 seconds.
- 2. Add Part B to Part A and mix with a mixer for 60 seconds.
- 3. Add Part C to Part (A+B) and mix with a mixer for 60 seconds.
- 4. Add Part D to the mixture (A+B+C) and mix for 60 seconds.
- 5. Add Part E to the mixture (A+B+C+D) and mix with a mixer for 20 seconds.
- 6. Weigh Part F and mix with a mixer for 30 seconds.
- 7. Add Part G to Part F and mix with a mixer for 10 seconds.
- 8. Add Part H to Part (F+G) and mix with a mixer for 10 seconds.
- 9. Add Part (F+G+H) and Part I to Part (A+B+C+D+E) and mix with a mixer for 10 seconds.
- 10. Press the mixture at 0.4 MPa twice for 2 seconds. <PHYSICAL PROPERTIES and STABILITY>

## Appearance: Cake

Hardness: 53.9 mN (GS-719N/Techrock Co., Ltd) Dropping test: No problem (30 cm, 2 times)



Note; The information is provided based upon our technical data and present knowledge. However, we make no warranties, expressed or implied, and assume no liabilities in connection with any use of the information with respect to specific property, safety and suitability for a specific application. It is also not guaranteed that use of the information does not fall within the scope of any intellectual property rights.