

PRESSED POWDER FOUNDATION SYPF-K

Powder foundation containing **AMIHOPE™ SB-103** gives creamy and soft feeling on the skin and provides a wrinkle-blurring effect.

	Trade Name	INCI Name	wt%	Function
A	Talc JA-24R *1	Talc	16.1	Extender
	NAI-SERICITE FSE *2	Mica, Disodium Stearoyl Glutamate, Aluminium Hydroxide	32.0	Extender
	NAI-MICA Y-2300 *2	Mica, Disodium Stearoyl Glutamate, Aluminium Hydroxide	20.0	Extender
	NAI-TR-10 *2	Titanium Dioxide, Aluminum Hydroxide, Disodium Stearoyl Glutamate	8.0	Pigment, UV scattering agent
	MT-100Z *3	Titanium Dioxide, Aluminum Stearate	3.0	UV scattering agent
	MZ 500 *3	Zinc Oxide	2.0	UV scattering agent
	NAI-RPS-10 *2	Iron Oxides, Disodium Stearoyl Glutamate, Aluminum Hydroxide	0.4	Pigment
	NAI-YP-10 *2	Iron Oxides, Disodium Stearoyl Glutamate, Aluminum Hydroxide	1.0	Pigment
	NAI-BP-10 *2	Iron Oxides, Disodium Stearoyl Glutamate, Aluminum Hydroxide	0.2	Pigment
	AMIHOPE™ SB-103	Tapioca Starch, Lauroyl Lysine	10.0	Sensory Improver
B	CEH *4	Cetyl Ethylhexanoate	3.3	Emollient, Binder
	COSMOL 44V *5	Polyglyceryl-2 Tetraisostearate	2.0	Emollient, Binder
	COSMOL 168ARV *5	Dipentaerythryl Hexahydroxystearate / Hexastearate / Heaerosinate	0.7	Emollient, Binder
	MORESCO WHITE P-70 *6	Mineral oil	1.3	Emollient, Binder
	NATURAL VITAMIN E *7	Tocopherol	0.01	Antioxidant
		Total	100.0	

*1 ASADA MILLING, *2 MIYOSHI KASEI, *3 TAYCA, *4 KOKYU ALCOHOL KOGYO, *5 NISSHIN OILLIO GROUP, *6 MORESCO, *7 TAMA SEIKAGAKU

<PROCEDURE>

1. Dissolve part B with heating.
2. Weigh all ingredients of part A and pulverize them with mixer for 30 seconds.
3. Add part B to part A and pulverize the mixture for around 1 minutes.
4. Pass the powder through a sieve (MESH No:100, OPENING:150µm).
5. Press it at 0.3MPa twice for 2 seconds each.

<PHYSICAL PROPERTIES and STABILITY>

Appearance: Beige cake

Hardness: 57.4 mN (GS-719N / Techrock Co.,Ltd.)



Note; The information is provided based upon our technical data and present knowledge. However, we make no warranties, expressed or implied, and assume no liabilities in connection with any use of the information with respect to specific property, safety and suitability for a specific application. It is also not guaranteed that use of the information does not fall within the scope of any intellectual property rights.