

MATTE LIP COLOR <Stick> TG22-MTLP

ELDEW™ PS-203R provides matte lipstick with excellent moisturizing property and smoothness.

	Trade name	INCI Name	wt %	Function
A	ELDEW™ PS-203R	Phytosteryl/Octyldodecyl Lauroyl Glutamate	10.0	Emollient Pigment dispersant
	KALKOL 200GD *1	Octyldodecanol	10.0	Emollient
	SALACOS P-8 *2	Ethylhexyl Palmitate	4.0	Emollient
	TCG-M *3	Caprylic/Capric Triglyceride	26.0	Emollient
	CERESIN #810 *4	Ceresin	6.0	Binder
	PMWAX 82 *4	Polyethylene, Microcrystalline Wax	2.0	Binder
	CARNAUBA WAX R-100 *5	Carnauba Wax	1.0	Binder
	SR BEESWAX-PA *6	Beeswax	5.0	Binder
	CANDELILLA WAX MK-2 *5	Candelilla Wax	2.0	Binder
B	COVALIGHT WHITE OS 987 AS *7	Titanium Dioxide, Triethoxycaprylylsilane, Isononyl Isononanoate, Ethylene/Propylene/Styrene Copolymer, Sorbitan Oleate	2.0	Pigment
	COVALIGHT RED OS 381 AS *7	Iron Oxide, Triethoxycaprylylsilane, Isononyl Isononanoate, Ethylene/Propylene/Styrene Copolymer, Sorbitan Oleate	6.0	Pigment
	DK PGT PASTE R7 *8	Polyglyceryl-2 Triisostearate, RED 7 (CI 15850)	2.0	Colorant
	GODD BALL G-6C *9	Silica	5.0	Texture modifier
	WHITE CLAY *10	Kaolin	19.0	Texture modifier
		Total	100.0	

*1 Kao, *2 Nissin Oillio, *3 Kokyu Alcohol Kogyo, *4 Nikko Rica, *5 Yokozeki Oil & Fat Industries, *6 Croda, *7 Sensient Beauty, *8 Daito Kasei Kogyo, *9 Suzukiyushi Industrial, *10 Alban Muller

<PROCEDURE>

1. Mix part A uniformly at over 90°C.
2. Mix part B uniformly at room temperature.
3. Add part B into part A and mix with hands, then disperse part (A+B) with a roller mill 3 times.
4. Heat part (A+B) at over 80°C and defoam.
5. Fill part (A+B) into a mold at 75°C.
6. Cool 5 in a freezer for 30 minutes and remove it from the mold at room temperature.

<PHYSICAL PROPERTIES and STABILITY>

Appearance: Stick

Stability: 5°C, 25°C, 45°C, Cycle (-5~40°C), 3 Months



Note; The information is provided based upon our technical data and present knowledge. However, we make no warranties, expressed or implied, and assume no liabilities in connection with any use of the information with respect to specific property, safety and suitability for a specific application. It is also not guaranteed that use of the information does not fall within the scope of any intellectual property rights.